

Tentative

## Low Fouling RO Elements


### TML

Type	Diameter inch	Membrane Area ft <sup>2</sup> (m <sup>2</sup> )	Salt Rejection %	Product Flow Rate gpd (m <sup>3</sup> /d)
TML10	4"	73 (7)	99.7	1,850 (7.0)
TML20-370	8"	370 (34)	99.7	9,500 (36)
TML20-400	8"	400 (37)	99.7	10,200 (39)

<b>1. Membrane Type</b>		Cross Linked Fully Aromatic Polyamide Composite
<b>2. Test Conditions</b>	Feed Water Pressure Feed Water Temperature Feed Water Concentration Recovery Rate Feed Water pH	225 psi (1.55 MPa) 77 °F (25 °C) 2,000 mg/l NaCl 15 % 7
<b>3. Minimum Salt Rejection</b>		99.0 %
<b>4. Minimum Product Flow Rate</b>		1,450 gpd (5.5 m <sup>3</sup> /d) (TML10) 7,500 gpd (28 m <sup>3</sup> /d) (TML20-370) 8,200 gpd (31 m <sup>3</sup> /d) (TML20-400)

### Dimensions

All dimensions shown in inches (millimeter).



## Operating Limits

Maximum Operating Pressure	600 psi (4.1 MPa)
Maximum Feed Water Temperature	113 °F (45 °C)
Maximum Feed Water SDI <sub>15</sub>	5
Feed Water Chlorine Concentration	Not Detectable
Feed Water pH Range, Continuous Operation	2-11
Feed Water pH Range, Chemical Cleaning	1-12
Maximum Pressure Drop per Element	20 psi (0.14 MPa)
Maximum Pressure Drop per Vessel	60 psi (0.4 MPa)

## Operating Information

1. For the recommended design range, please consult the latest Toray technical bulletin, design guidelines, computer design program, and/or call an application specialist. If the operating limits given in this Product Information Bulletin are not strictly followed, the Limited Warranty will be null and void.
2. All elements are wet tested, treated with a 1% by weight percent sodium bisulfite storage solution, and then vacuum packed in oxygen barrier bags. To prevent biological growth during short term storage, shipment, or system shutdown, it is recommended that Toray elements be immersed in a protective solution containing 500 - 1,000 ppm of sodium bisulfite (food grade) dissolved in permeate.
3. Permeate from the first hour of operation shall be discarded.
4. The customer is fully responsible for the effects of chemicals that are incompatible with the elements. Their use will void the element Limited Warranty.

## Notice

1. Toray accepts no responsibility for results obtained by the application of this information or the safety or suitability of Toray's products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product combination for their own purposes.
2. All data may change without prior notice, due to technical modifications or production changes.

**Asia and Oceania:**  
**Toray Industries, Inc.**  
Membrane Products Department

8-1, Mihama 1-chome  
Urayasu, Chiba 279-8555, Japan  
Tel: +81 47 350 6030  
Fax: +81 47 350 6066  
<http://www.toray-membrane.com>

**Americas:**  
**Toray Membrane America, Inc.**  
Sales Office

12520 High Bluff Drive, Suite 120  
San Diego, CA 92130, U.S.A.  
Tel: +1 858 523 0476  
Fax: +1 858 523 0861

**Europe, Middle East and Africa:**  
**Toray Membrane Europe AG**

Grabenackerstrasse 8  
CH-4142 Münchenstein 1, Switzerland  
Tel: +41 61 415 87 10  
Fax: +41 61 415 87 20